20

25

What is claimed is:

- A method for forming an optical blank, the method comprising: providing soot particles;
 spray-drying the soot particles to form an agglomerate; dry-pressing the agglomerate to form a green body; and heating the green body to form a glass object.
 - 2. The method of claim 1, wherein the step of providing soot particles includes forming soot particles as a by-product of a flame hydrolysis process.
 - 3. The method of claim 2, further comprising the step of cleaning the green body to remove impurities.
 - 4. The method of claim 3, wherein the step of cleaning further comprises: disposing the green body in a high temperature chlorine gas atmosphere, the high temperature being lower than a sintering temperature; and treating the green body by allowing the chlorine gas to react with the impurities for a pre-determined time.
 - 5. The method of claim 4, wherein the high temperature is between 700°C and 1100°C.
 - 6. The method of claim 1, wherein the step of spray-drying further comprises: mixing the soot particles with water to form a slurry; discharging the slurry through a nozzle to form a plurality of slurry droplets; and drying the plurality of droplets to form the agglomerate.
 - 7. The method of claim 6 wherein the slurry does not include a dispersant.
- 30 8. The method of claim 7, wherein the agglomerate includes a plurality of silica containing solid spheres.

- 9. The method of claim 8, wherein the plurality of silica containing solid spheres have a diameter substantially within the range of 10 to 200 microns.
- 10. The method of claim 6, wherein the slurry includes a dispersant.

5

30

- 11. The method of claim 10, wherein the agglomerate includes a plurality of silica containing hollow spheres.
- 12. The method of claim 11, wherein the plurality of silica containing hollow spheres have a diameter substantially within the range of 10 to 200 microns.
- 13. The method of claim 10, wherein the dispersant includes ammonia hydroxide.
- 14. The method of claim 6, wherein the slurry is substantially a 50 weight percent soot suspension.
- 15. The method of claim 6, wherein the slurry includes a binder agent.
- 16. The method of claim 15, wherein the binder agent is substantially a 3 weight percentpolyethylene glycol suspension.
 - 17. The method of claim 1, wherein the agglomerate includes granules having a diameter substantially within the range of 10 to 200 microns.
- 25 18. The method of claim 1, wherein the agglomerate has a bulk density in the approximate range between 30 50%.
 - 19. The method of claim 1, wherein the step of dry-pressing includes dry pressing the agglomerate at pressure substantially in the range between 1,000Psi and 10,000Psi.
 - 20. The method of claim 19, wherein the step of dry-pressing includes the step of forming pellets.

- 21. The method of claim 1, wherein the step of heating includes the step of sintering the green body.
- 22. The method of claim 21, wherein the step of sintering the green body is performed at a temperature above 1100°C.
 - 23. The method of claim 22, wherein the green body is sintered at a temperature of approximately 1400°C.
 - 24. The method of claim 22, wherein the green body is sintered at a temperature of approximately 1500°C.
 - 25. The method of claim 21, wherein the step of sintering further comprises:

 disposing the green body in a high temperature chlorine gas atmosphere, the high
 temperature being lower than a sintering temperature; and
 treating the green body by allowing the chlorine gas to react with the impurities for a
 pre-determined time.
- 26. The method of claim 21, wherein the step of sintering is performed in a substantial vacuum.
 - 27. The method of claim 21, wherein the step of sintering is performed in a helium atmosphere.
- 28. The method of claim 1, wherein the step of heating includes heating the green body to a temperature substantially within a range between 1350°C and 1800°C.
 - 29. The method of claim 28, wherein the step of heating is performed in a vacuum chamber.
- 30. The method of claim 28, wherein the step of heating is performed in a helium atmosphere.